

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
13 May 2004 (13.05.2004)

PCT

(10) International Publication Number  
WO 2004/040061 A1

(51) International Patent Classification<sup>7</sup>: D21H 17/68,  
C01B 39/02

(74) Agents: MCCALLUM, Graeme, David et al.; Lloyd  
Wise, McNeight & Lawrence, Highbank House, Exchange  
Street, Stockport, Cheshire SK3 0ET (GB).

(21) International Application Number:  
PCT/GB2003/004593

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE,  
GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR,  
KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK,  
MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT,  
RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR,  
TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 22 October 2003 (22.10.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0225177.5 30 October 2002 (30.10.2002) GB

(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): INEOS  
SILICAS LIMITED [GB/GB]; Bank Quay, Warrington,  
Cheshire WA5 1AB (GB).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): TOFT, Alexis,  
John [GB/GB]; Parkside, Stockport Road, Thelwall, War-  
rington, Cheshire WA4 2SZ (GB). STEBBING, Simon,  
Richard [GB/GB]; 53 Kinross Close, Fearnhead, War-  
rington, Cheshire WA2 0UT (GB). ELLISON, Stephen,  
George [GB/GB]; 6 Camborne Road, Burtonwood, War-  
rington, Cheshire WA5 5LX (GB).

Published:

— with international search report  
— before the expiration of the time limit for amending the  
claims and to be republished in the event of receipt of  
amendments

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: STABILISED ALUMINOSILICATE SLURRIES

(57) Abstract: An aqueous slurry according to the invention comprises (a) a crystalline aluminosilicate represented by the empirical formula  $M_{2n}O \cdot Al_2O_3 \cdot xSiO_2 \cdot yH_2O$  wherein M represents a first metal moiety, said first metal having a valency of n, x indicates the ratio of atoms of silicon to atoms of aluminium and y indicates the ratio of molecules of water to atoms of aluminium, (b) a salt of a second metal selected from the group consisting of Group III metals, metallic elements of Group IV, magnesium, titanium, chromium, iron, nickel, copper, zinc, zirconium and silver, said salt of a second metal being present in an amount which is sufficient to replace from about 2.0 to about 40 per cent by weight of the first metal moiety, and (c) particulate silica having a BET surface area greater than 500 m<sup>2</sup>/g and a pore volume, as measured by nitrogen manometry of less than 2.1 cm<sup>3</sup>/g. The slurry is stable on storage but has a low viscosity at low shear rate.

WO 2004/040061 A1

10/533318

JC17 Rec'd PCT/PTO 29 APR 2005

## STABILISED ALUMINOSILICATE SLURRIES

This invention relates to aqueous slurries of crystalline aluminosilicates and in particular to crystalline aluminosilicate slurries having controlled rheological properties.

5

Crystalline aluminosilicates, or zeolites, have found use as fillers in such applications as the manufacture of paper. For such use, it is convenient to transport the zeolite in bulk in the form of an aqueous slurry. Particularly useful aqueous zeolite slurries having a relatively low pH value and containing a multivalent salt in addition to the zeolite are described in PCT application published as WO 01/94512. These slurries are stable and do not settle on standing but, because they have a lightly gelled structure, they can sometimes be difficult to fully discharge from a vessel.


An object of this invention is to provide a modified version of such a slurry having a structure which is resistant to settling but is readily capable of being discharged from a vessel.

15

According to the invention, an aqueous slurry comprises

(a) a crystalline aluminosilicate represented by the empirical formula

20



wherein M represents a first metal moiety, said first metal having a valency of n, x indicates the ratio of atoms of silicon to atoms of aluminium and y indicates the ratio of molecules of water to atoms of aluminium,

(b) a salt of a second metal selected from the group consisting of Group III metals, metallic elements of Group IV, magnesium, titanium, chromium, iron, nickel, copper, zinc, zirconium and silver, said salt of a second metal being present in an amount which is sufficient to replace from about 2.0 to about 40 per cent by weight of the first metal moiety, and

(c) particulate silica having a BET surface area greater than 500 m<sup>2</sup>/g and a pore volume, as measured by nitrogen manometry of less than 2.1 cm<sup>3</sup>/g.

30

The above form of empirical formula is used for simplicity in expressing the molar ratios of the components, but it can be seen that the ratio of Si atoms to Al atoms in this formula is equal to x/2 and the ratio of water molecules to Al atoms is equal to y/2.

35

The first metal M can be any metal capable of forming a crystalline aluminosilicate structure having the above empirical formula. Preferably, M is an alkali metal and the preferred alkali metal is sodium.

The crystalline aluminosilicates used in the invention are usually known as zeolites and can have the structure of any of the known zeolites. The structure and characteristics of many zeolites are described in the standard work "Zeolite Molecular Sieves" by Donald W. Breck, published by Robert E. Krieger Publishing Company. Usually, the value of x in the above empirical formula is in the range 1.5 to 10. The value of y, which represents the amount of water contained in the voids of the zeolite, can vary widely. In anhydrous material  $y = 0$  and, in fully hydrated zeolites, y is typically up to 5.

Zeolites useful in this invention may be based on naturally-occurring or synthetic aluminosilicates and the preferred forms of zeolite have the structure known as zeolite P, zeolite X or zeolite A. Particularly preferred forms of zeolite are those disclosed in EP-A-0 384 070, EP-A-0 565 364, EP-A-0 697 010, EP-A-0 742 780, WO-A-96/14270, WO-A-96/34828 and WO-A- 97/06102, the entire contents of which are incorporated herein by this reference. The zeolite P described in EP-A-0 384 070 has the empirical formula given above in which M represents an alkali metal and x has a value up to 2.66, preferably in the range 1.8 to 2.66, and has a structure which is particularly useful in the present invention.

The preferred amount of the salt of a second metal used to prepare mixtures used in the invention depends upon a number of factors, such as the actual second metal selected, the actual crystalline aluminosilicate chosen and the desired effect to be achieved (in particular, the desired pH of the slurry). Useful mixtures contain an amount of second metal salt sufficient to replace from 3.0 to 30 per cent by weight of first metal, and, more preferably, from 3.0 to 20 per cent by weight of the first metal.

The appropriate amount of salt of a second metal in the mixture used in the invention, expressed in grams, depends upon the composition of the zeolite and the charge on the second metal but is readily calculated by a skilled person. For example, a zeolite having the empirical formula



(anhydrous type A zeolite) contains 16.2 g of Na per 100 g of zeolite. An aluminium ion is capable of replacing three sodium ions. Hence, making allowance for the atomic weights of sodium and aluminium, it can be calculated that a mixture containing 100 g of anhydrous zeolite A and 0.317 g Al in the form of a suitable salt is a mixture suitable for use in the invention and containing sufficient salt of a second metal (i.e. aluminium) to replace 5 per cent by weight of the first metal moiety (i.e. sodium).

It has been observed that a salt of a second metal wherein the ion of the second metal has a relatively small size or a relatively high charge is more effective as a means of controlling the pH of the zeolite slurry. Consequently, the effect of the metal salt on the pH of the slurry is more marked when the salt of a second metal is a salt of aluminium than when it is a salt of magnesium and the effect is more marked for salts of magnesium than for salts of zinc. The preferred second metals for use in the invention are aluminium, zirconium and tin.

Slurries useful in the paper industry preferably have an approximately neutral pH. Particularly useful slurries of this invention contain an amount of the second metal which is sufficient to produce a slurry having a pH in the range 6 to 9, preferably in the range 7 to 9.

The particle size of the crystalline aluminosilicates used in the slurries of this invention is adjusted to suit the intended use. Typically, the volume average particle size will be greater than 0.1  $\mu\text{m}$  and, usually, less than 20  $\mu\text{m}$ . More preferably, the crystalline aluminosilicates will have a volume average particle size in the range 0.5 to 10  $\mu\text{m}$ . For use as a filler for papers, the crystalline aluminosilicate preferably has a volume average particle size in the range 1 to 5  $\mu\text{m}$ .

Various methods of assessing particle size are known and all give slightly different results. In the present invention, a size distribution is obtained by light scattering from particles dispersed by ultrasound in demineralised water using a Malvern Mastersizer®. The volume average particle size is the average particle size at 50 per cent cumulative volume as determined from the distribution.

The amount of crystalline aluminosilicate, expressed as dry weight of aluminosilicate present in the slurry is usually above 20 per cent by weight and often above 30 per cent by weight. The upper practical limit on the amount of aluminosilicate in the slurry will depend upon the viscosity of the slurry, which is likely to be too high for use in many applications when more than 65 per cent dry weight of aluminosilicate is present. Generally, useful slurries consisting essentially of crystalline aluminosilicate, salt of a second metal, silica and water, according to this invention, will contain not more than 50 per cent by weight of aluminosilicate (on a dry basis). For the purposes of this invention dry aluminosilicate is considered to be aluminosilicate which has been heated at 105° C to constant weight.

The slurry of the invention contains a salt of a second metal as hereinbefore specified. Mixtures of more than one salt of a second metal (as defined) or salts of more than one second metal (as defined) can be used. Suitable salts include halides, such as chlorides (e.g. stannic chloride), nitrates, and, preferably, sulphates (e.g. aluminium sulphate, magnesium sulphate, zinc sulphate or zirconium sulphate).

The slurry also contains silica having a BET surface area greater than 500 m<sup>2</sup>/g. Preferably the silica has a BET surface area greater than 600 m<sup>2</sup>/g. Usually the surface area is less than 1200 m<sup>2</sup>/g.

The silica also has a pore volume as measured by nitrogen manometry of less than 2.1 cm<sup>3</sup>/g. Preferably, the pore volume is less than 1.2 cm<sup>3</sup>/g.

Preferably, the silica is silica gel or a precipitated silica.

The silica preferably has a volume average particle size in the range 0.5 to 30 µm, as measured by Malvern Mastersizer<sup>®</sup>. More preferably, the volume average particle size of the silica is in the range 2 to 15 µm.

The silica is preferably present in the slurry in an amount in the range 0.2 to 40 per cent by weight with respect to the dry weight of crystalline aluminosilicate. More preferably, the amount of silica present is in the range 0.5 to 15 per cent by weight with respect to dry weight of crystalline aluminosilicate and frequently, the amount of silica used is in the range 1.0 to 5.0 by weight with respect to dry weight of crystalline aluminosilicate.

The crystalline aluminosilicate used in the invention can be prepared by a conventional process. For example, a zeolite of type A can be prepared by mixing together sodium aluminate and sodium silicate at a temperature within the range of ambient temperature up to boiling point to form a gel, ageing the gel with stirring at a temperature usually in the range 70 to 95° C, separating the crystalline sodium aluminosilicate thus formed, washing, generally at a pH in the range 10 to 12.5, and drying. Zeolite of type P can be prepared by a similar process but zeolite type P formation is induced by the addition of type P seeds to the mixture of sodium aluminate and sodium silicate.

The slurry of the invention can be prepared in a number of ways. The crystalline aluminosilicate, salt of a second metal and water can be mixed in any order. A preferred method, however, comprises forming a solution of salt of a second metal at an

appropriate concentration, adding the crystalline aluminosilicate with stirring and subsequently adding the silica, while the stirring is continued.

The following tests have been used in this invention.

5

#### BET Surface Area and Pore Volume

Surface area of the silicas were measured using standard nitrogen adsorption methods of Brunauer, Emmett and Teller (BET) using a multi-point method with an ASAP 2400 apparatus supplied by Micromeritics of USA. The method is consistent with the paper by S. Brunauer, P.H. Emmett and E. Teller, J. Am. Chem. Soc., 60, 309 (1938). The pore volume was determined by a single point method as described in the operation manual for the ASAP 2400 apparatus. Samples are outgassed under vacuum at 270° C for 1 hour before measurement at about -196° C.

#### 15 Volume average particle size

The volume average particle size of the silica is determined using a Malvern Mastersizer® model S, with a 300 RF lens and MS17 sample presentation unit. This instrument, made by Malvern Instruments, Malvern, Worcestershire uses the principle of Fraunhofer diffraction, utilising a low power He/Ne laser. Before measurement the sample is dispersed ultrasonically at 25 W ultrasound power in demineralised water for 5 minutes to form an aqueous suspension. The Malvern Mastersizer® measures the volume particle size distribution of the silica. The volume average particle size ( $d_{50}$ ) or 50 percentile is easily obtained from the data generated by the instrument. Other percentiles, such as the 90 percentile ( $d_{90}$ ), are readily obtained.

25

The invention is illustrated by the following non-limiting examples.

### EXAMPLES

#### 30 Example 1

Three 100g slurries were prepared with the compositions given in Table 1 below.

35

TABLE 1

Sample	A	B	C
Demineralised Water	57.8	57.8	57.8
$\text{Al}_2(\text{SO}_4)_3 \cdot 14 \text{H}_2\text{O}$	1.7	1.7	1.7
Zeolite A24 (water content 7.03% by drying at 105° C)	40.5	39.5	0
Zeolite A28 (water content 13.35% by drying at 105° C)	0	0	39.5
Silica	0	1.0	1.0

The amounts given above are parts by weight.

Zeolite A24 is a P type zeolite sold by INEOS Silicas Limited under the trade mark Doucil A24. It had a volume average particle size as measured by Malvern Mastersizer® of 1.5  $\mu\text{m}$ .

Zeolite A28 is a P type zeolite sold by INEOS Silicas Limited under the trade mark Doucil A28. It had a volume average particle size as measured by Malvern Mastersizer® of 2.8  $\mu\text{m}$ .

The silica was a silica gel sold by INEOS Silicas Limited under the Trade Name Sorbosil AC30. It had a volume average particle size of 7.9  $\mu\text{m}$ , a pore volume to nitrogen of 0.39  $\text{cm}^3\text{g}^{-1}$  and BET surface area of 725  $\text{m}^2\text{g}^{-1}$ .

Three small portions were taken from each of the slurries immediately after preparation and the rheological properties of the remaining slurries were determined using a Mettler Toledo RM 180 Rheomat rheometer, at  $22 \pm 1^\circ \text{C}$ , with a Mooney cup and bob geometry. The samples were shaken by hand prior to measurement but were not sheared vigorously. The rheometer programme consisted of shearing the sample at a set shear rate for 30 seconds, after which a shear stress measurement was taken at that shear rate. Measurements were taken at 10, 20, 30, 40, 60, 100, 200, 350 and 500  $\text{s}^{-1}$ . The rheological properties of the small portions were similarly measured at 4 days, 24 days and 60 days after the slurries were prepared.

Sample A, initially and after storage, had a much higher viscosity than the other samples at all the measured shear rates. Importantly, the viscosity at low shear for Samples B and C was much lower than for Sample A. This is illustrated by the results for viscosity at a shear rate of 20  $\text{s}^{-1}$  shown in Table 2 below.

TABLE 2

Sample		A	B	C
Viscosity at 20 s <sup>-1</sup> (Pa s)	Initially	0.55	0.06	0.02
	After 4 days	0.58	0.06	0.10
	After 24 days	0.62	0.15	0.07
	After 60 days	0.69	0.25	0.12

All stock slurries showed a very slight sedimentation within 1 day, but this did not change on storage over 2 months.

5

Material similar to Sample A was stored in a large tank and it was found that it was difficult to satisfactorily discharge the bulk of the material from the tank. In contrast, material similar to Sample B was readily discharged from a tank after storage, leaving only a minimal heel.

10

### Example 2

100g slurries were prepared with the compositions given in Table 3 below.

TABLE 3

Sample	D	E	F
Demineralised Water	58.0	57.6	57.6
Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub> .14 H <sub>2</sub> O	1.5	1.5	1.5
Zeolite A24 (water content 7.03% by heating at 105° C)	40.5	40.2	40.2
Silica – Sorbosil AC30	-	0.7	-
Silica – Gasil™ GM2	-	-	0.7

15 The amounts given above are parts by weight.

The zeolite and silica (Sorbosil AC30) were as used in Example 1. Gasil™ GM2 was a silica gel sold by INEOS Silicas Limited having a volume average particle size of 7.3 µm, a pore volume to nitrogen of 0.37 cm<sup>3</sup>g<sup>-1</sup> and a BET surface area of 691 m<sup>2</sup>g<sup>-1</sup>.

20 The rheology profiles were measured as described in Example 1 on the samples 24 hours after preparation. The profiles of E and F were essentially similar to the profiles of



Samples B and C, with Sample D being similar to Sample A. The viscosities at 20 s<sup>-1</sup> were as follows:

	Sample D	0.54 Pa s
	Sample E	0.01 Pa s
5	Sample F	0.01 Pa s.

### Example 3

1 Kg slurries were prepared with the compositions in Table 4

TABLE 4

Sample	G	H	I	J
Demineralised Water	589.39	592.86	590.78	578.52
Second metal salt	15.91	12.44	14.52	26.78
Zeolite A24 (water content 3.6% by heating at 105° C)	387.7	387.7	387.7	387.7
Silica – Sorbosil AC30	7	7	7	7

10 The amounts given above are parts by weight.

The zeolite was as used in Example 1 except that the loss at 105 degrees C for the A24 zeolite was 3.6%. The Sorbosil AC30 used in this Example had a volume average particle size of 8.1 µm, a pore volume to nitrogen of 0.40 cm<sup>3</sup>g<sup>-1</sup> and BET surface area of 724 m<sup>2</sup>g<sup>-1</sup>.

15

The metal salt employed in each sample was as follows:

Sample G: Al<sub>2</sub>(SO<sub>4</sub>)<sub>3</sub>.16 H<sub>2</sub>O

Sample H: MgSO<sub>4</sub>.7 H<sub>2</sub>O

Sample I: ZnSO<sub>4</sub>.7 H<sub>2</sub>O

20 Sample J: Zr(SO<sub>4</sub>)<sub>2</sub> solution

All of the salts were added as a solid except zirconium sulphate which was added as a 53.4 wt% solution, the amount of zirconium in this solution being determined using ICP atomic emission spectroscopy. The concentration of the metal cation coming from the added salt is the same in all slurries.

In addition to the above samples, 1 Kg slurries were prepared as specified in Table 4 except that the silica was omitted with corresponding adjustment of the demineralised water content – these are referred to below as samples Gc, Hc, Ic and Jc.

5 Viscosity results (in Pa s) at a shear rate of  $20 \text{ s}^{-1}$ , obtained using the procedure described in example 1, are shown in Table 5 below for 4 days and 14 days (where available) after preparation of the slurries referred to above.

TABLE 5

Sample	G	Gc	H	Hc	I	Ic	J	Jc
4 days	0.06	0.40	0.07	0.34	0.02	0.31	0.04	0.36
14 days	0.14	0.42	0.08	0.42	-	-	-	-

CLAIMS

1. An aqueous slurry comprising
  - (a) a crystalline aluminosilicate represented by the empirical formula
$$M_{2/n}O \cdot Al_2O_3 \cdot xSiO_2 \cdot yH_2O$$
- 5 wherein M represents a first metal moiety, said first metal having a valency of n, x indicates the ratio of atoms of silicon to atoms of aluminium and y indicates the ratio of molecules of water to atoms of aluminium,
  - (b) a salt of a second metal selected from the group consisting of Group III metals, metallic elements of Group IV, magnesium, titanium, chromium, iron, nickel,
  - 10 copper, zinc, zirconium and silver, said salt of a second metal being present in an amount which is sufficient to replace from about 2.0 to about 40 per cent by weight of the first metal moiety, and
  - (c) particulate silica having a BET surface area greater than 500 m<sup>2</sup>/g and a pore volume, as measured by nitrogen manometry of less than 2.1 cm<sup>3</sup>/g.
- 15 2. An aqueous slurry according to claim 1 characterised in that M is sodium.
3. An aqueous slurry according to claim 1 or 2 characterised in that the crystalline aluminosilicate is a zeolite P, zeolite A or zeolite X.
- 20 4. An aqueous slurry according to any one of the preceding claims characterised in that the second metal is aluminium, zirconium or tin.
5. An aqueous slurry according to any one of the preceding claims characterised in
- 25 that it has a pH in the range 6 to 9.
6. An aqueous slurry according to any one of the preceding claims characterised in that the crystalline aluminosilicate has a volume average particle size in the range 0.1 to 20 µm.
- 30 7. An aqueous slurry according to any one of the preceding claims characterised in that the amount of crystalline aluminosilicate present in the slurry is in the range 20 to 50 per cent by weight calculated as dry aluminosilicate.
- 35 8. An aqueous slurry according to any one of the preceding claims characterised in that the silica has a BET surface area greater than 600 m<sup>2</sup>/g.

9. An aqueous slurry according to any one of the preceding claims characterised in that the silica has a pore volume of less than  $1.2 \text{ cm}^3/\text{g}$ .
10. An aqueous slurry according to any one of the preceding claims characterised in that the silica has a volume average particle size in the range  $0.5$  to  $30 \text{ }\mu\text{m}$ .
11. An aqueous slurry according to any one of the preceding claims characterised in that the amount of silica present in the slurry is in the range  $0.2$  to  $40$  per cent by weight with respect to dry weight of crystalline aluminosilicate present.
12. An aqueous slurry according to any one of the preceding claims in which the metal salt is a halide, a nitrate or a sulphate.

## INTERNATIONAL SEARCH REPORT

Application No  
PCT/GB J3/04593A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 D21H17/68 C01B39/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

PAJ, EPO-Internal, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 01 94512 A (INEOS SILICAS LTD ; ARAYA ABRAHAM (GB)) 13 December 2001 (2001-12-13) cited in the application abstract claims 1-5,7,9,12 ---	1-12
A	DATABASE WPI Section Ch, Week 198628 Derwent Publications Ltd., London, GB; Class F09, AN 1986-178224 XP002271505 & JP 61 097499 A (ASAHI GLASS CO LTD), 15 May 1986 (1986-05-15) abstract --- -/--	1-12

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

25 February 2004

Date of mailing of the international search report

08/03/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Naeslund, P

## INTERNATIONAL SEARCH REPORT

Application No  
PCT/JP 93/04593

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Section Ch, Week 199550 Derwent Publications Ltd., London, GB; Class A97, AN 1995-390591 XP002271506 &amp; JP 07 268400 A (LION CORP), 17 October 1995 (1995-10-17) abstract</p> <p>---</p>	1-12
A	<p>DATABASE WPI Section Ch, Week 199420 Derwent Publications Ltd., London, GB; Class H04, AN 1994-163245 XP002271507 &amp; JP 06 106064 A (COSMO OIL CO LTD), 19 April 1994 (1994-04-19) abstract</p> <p>---</p>	1-12
A	<p>DATABASE WPI Section Ch, Week 198621 Derwent Publications Ltd., London, GB; Class E33, AN 1986-134059 XP002271508 &amp; JP 61 070098 A (ASAHI GLASS CO LTD), 10 April 1986 (1986-04-10) abstract</p> <p>---</p>	1
A	<p>EP 0 384 070 A (UNILEVER PLC ;UNILEVER NV (NL)) 29 August 1990 (1990-08-29) cited in the application the whole document</p> <p>---</p>	1-12
A	<p>EP 0 565 364 A (CROSFIELD JOSEPH &amp; SONS) 13 October 1993 (1993-10-13) cited in the application page 2, line 41 -page 3, line 32 examples 1-5</p> <p>-----</p>	1-5

# INTERNATIONAL QUAL SEARCH REPORT

Information on patent family members

Application No  
PCT/GU 3/04593

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0194512	A	13-12-2001	AU 6248701 A BR 0111324 A CN 1432056 T EP 1294840 A1 WO 0194512 A1 JP 2003535797 T US 2003148876 A1	17-12-2001 03-06-2003 23-07-2003 26-03-2003 13-12-2001 02-12-2003 07-08-2003
JP 61097499	A	15-05-1986	NONE	
JP 7268400	A	17-10-1995	NONE	
JP 6106064	A	19-04-1994	NONE	
JP 61070098	A	10-04-1986	NONE	
EP 0384070	A	29-08-1990	AT 127514 T AU 631143 B2 AU 4396689 A BR 8905601 A CA 2001927 A1 DE 68924152 D1 EP 0384070 A2 ES 2078244 T3 GR 3017709 T3 JP 2173094 A JP 2759096 B2 US 5374370 A US 5512266 A ZA 8908383 A	15-09-1995 19-11-1992 10-05-1990 29-05-1990 03-05-1990 12-10-1995 29-08-1990 16-12-1995 31-01-1996 04-07-1990 28-05-1998 20-12-1994 30-04-1996 31-07-1991
EP 0565364	A	13-10-1993	AT 173284 T AU 3678393 A BR 9301471 A CA 2093303 A1 CN 1079714 A , B CZ 9300619 A3 DE 69321987 D1 DE 69321987 T2 DK 565364 T3 EP 0565364 A1 ES 2123618 T3 FI 931572 A HU 66323 A2 JP 2523433 B2 JP 6115926 A KR 9700481 B1 MX 9302036 A1 PL 298425 A1 SK 32593 A3 TR 26679 A US 5362466 A US 2002076374 A1 ZA 9302543 A	15-11-1998 14-10-1993 13-10-1993 10-10-1993 22-12-1993 16-02-1994 17-12-1998 01-04-1999 26-07-1999 13-10-1993 16-01-1999 10-10-1993 28-11-1994 07-08-1996 26-04-1994 13-01-1997 01-12-1993 02-11-1993 10-11-1993 15-03-1995 08-11-1994 20-06-2002 08-10-1994

# INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/JP 03/04593

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 D21H17/68 C01B39/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

PAJ, EPO-Internal, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 01 94512 A (INEOS SILICAS LTD ; ARAYA ABRAHAM (GB)) 13 December 2001 (2001-12-13) cited in the application abstract claims 1-5, 7, 9, 12	1-12
A	DATABASE WPI Section Ch, Week 198628 Derwent Publications Ltd., London, GB; Class F09, AN 1986-178224 XP002271505 & JP 61 097499 A (ASAHI GLASS CO LTD), 15 May 1986 (1986-05-15) abstract	1-12

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \* & \* document member of the same patent family

Date of the actual completion of the international search

25 February 2004

Date of mailing of the international search report

08/03/2004

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Naeslund, P



## INTERNATIONAL SEARCH REPORT

Int. Application No  
PCT/JP 93/04593

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE WPI Section Ch, Week 199550 Derwent Publications Ltd., London, GB; Class A97, AN 1995-390591 XP002271506 & JP 07 268400 A (LION CORP), 17 October 1995 (1995-10-17) abstract -----	1-12
A	DATABASE WPI Section Ch, Week 199420 Derwent Publications Ltd., London, GB; Class H04, AN 1994-163245 XP002271507 & JP 06 106064 A (COSMO OIL CO LTD), 19 April 1994 (1994-04-19) abstract -----	1-12
A	DATABASE WPI Section Ch, Week 198621 Derwent Publications Ltd., London, GB; Class E33, AN 1986-134059 XP002271508 & JP 61 070098 A (ASAHI GLASS CO LTD), 10 April 1986 (1986-04-10) abstract -----	1
A	EP 0 384 070 A (UNILEVER PLC ;UNILEVER NV (NL)) 29 August 1990 (1990-08-29) cited in the application the whole document -----	1-12
A	EP 0 565 364 A (CROSFIELD JOSEPH & SONS) 13 October 1993 (1993-10-13) cited in the application page 2, line 41 -page 3, line 32 examples 1-5 -----	1-5

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Publication No

PCT/GU 3/04593

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0194512	A	13-12-2001	AU 6248701 A BR 0111324 A CN 1432056 T EP 1294840 A1 WO 0194512 A1 JP 2003535797 T US 2003148876 A1	17-12-2001 03-06-2003 23-07-2003 26-03-2003 13-12-2001 02-12-2003 07-08-2003
JP 61097499	A	15-05-1986	NONE	
JP 7268400	A	17-10-1995	NONE	
JP 6106064	A	19-04-1994	NONE	
JP 61070098	A	10-04-1986	NONE	
EP 0384070	A	29-08-1990	AT 127514 T AU 631143 B2 AU 4396689 A BR 8905601 A CA 2001927 A1 DE 68924152 D1 EP 0384070 A2 ES 2078244 T3 GR 3017709 T3 JP 2173094 A JP 2759096 B2 US 5374370 A US 5512266 A ZA 8908383 A	15-09-1995 19-11-1992 10-05-1990 29-05-1990 03-05-1990 12-10-1995 29-08-1990 16-12-1995 31-01-1996 04-07-1990 28-05-1998 20-12-1994 30-04-1996 31-07-1991
EP 0565364	A	13-10-1993	AT 173284 T AU 3678393 A BR 9301471 A CA 2093303 A1 CN 1079714 A , B CZ 9300619 A3 DE 69321987 D1 DE 69321987 T2 DK 565364 T3 EP 0565364 A1 ES 2123618 T3 FI 931572 A HU 66323 A2 JP 2523433 B2 JP 6115926 A KR 9700481 B1 MX 9302036 A1 PL 298425 A1 SK 32593 A3 TR 26679 A US 5362466 A US 2002076374 A1 ZA 9302543 A	15-11-1998 14-10-1993 13-10-1993 10-10-1993 22-12-1993 16-02-1994 17-12-1998 01-04-1999 26-07-1999 13-10-1993 16-01-1999 10-10-1993 28-11-1994 07-08-1996 26-04-1994 13-01-1997 01-12-1993 02-11-1993 10-11-1993 15-03-1995 08-11-1994 20-06-2002 08-10-1994